




ELEGANCE				
	Tecnical Specifications	Reference Standard	Standard Requirements	Test Results
	Water Absorption	UNI EN ISO 10545-03	≤ 0.5 %	≤ 0.5 %
	Breaking Strength	UNI EN ISO 10545-04	Minimum: 1300 N	3164 N
	Modulus of Rupture	UNI EN ISO 10545-04	Minimum: >35 N/mm²	48N/mm²
	Shock Resistance	UNI EN ISO 10545-05	Suggested Minimum: < 35 N/mm²	Resist
	Resistance to Deep Abrasion	UNI EN ISO 10545-06	Maximum 150 mm³	Max. 150 mm³
	Thermal Linear Expansion	UNI EN ISO 10545-07	Minimum for Floor Applications: Class 3	Resist
	Thermal Shock Resistance	UNI EN ISO 10545-09	Resistant	Resist
	Moisture Expansion	UNI EN ISO 10545-10	As Reported	0,1 mm/m
	Frost Resistance	UNI EN ISO 10545-12	As Reported	Resist
	Chemical Resistance	UNI EN ISO 10545-13	Domestic Chemical Products: UB / GB	GA
			Acids and Alkalis: As Reported	GLA
	Stain Resistance	UNI EN ISO 10545-14	Minimum: Class 3	Min. Class 3 (Nogal Class 2)
PEI	PEI Rating (Scratch Resistance)	ASTM C 1027	As Reported	IV
DCOF	Dynamic Coefficient of Friction (DCOF)	ANSI A137.1	For level Interior Spaces Expected to be Walked Upon When Wet	0,57
	Shade Variation	Not Available	As Reported	V2
	Thickness	Not Available	As Reported	11,2 mm.
	Number of Screens	Not Available	As Reported	14

1/2 BROKEN JOINT NOT RECOMMENDED.
MANUFACTURER RECOMMENDS 1/3 OR LESS
STAGGERED SPACING


IMPORTANT

Please note that fixing in a 50% staggered configuration is not recommended. We suggest the following fixing configurations for these ceramic materials:

NO 50%



YES 15%





Elegance

PORCELAIN





Natural



Roble



Nogal



White



Silver



Grey



Natural 8"x 45" RECTIFIED EDGE



Roble 8"x 45" RECTIFIED EDGE




Nogal 8"x 45" RECTIFIED EDGE



White 8"x 45" RECTIFIED EDGE



Silver 8"x 45" RECTIFIED EDGE



Grey 8"x 45" RECTIFIED EDGE



4"x 22.5"

Bullnose Available
in all colors



Natural



Roble



Nogal



White



Silver



Grey