



	<b>Technical Specifications</b>	Standard Requirements	Porcelain- Nat.	Ceramic- Glo.
٨	Water Absorption UNI EN ISO 10545-03	E≤0.5%	< 0.5%	<3%
<u> </u>	Breaking Strength UNI EN ISO 10545-04	≥ 1300 N	>1300 N	>1100 N
<u>↓</u>	Modulus of Rupture UNI EN ISO 10545-04	> 35 N/mm <sup>2</sup>	> 35 N/mm <sup>2</sup>	> 30 N/mm <sup>2</sup>
	Shock Resistance UNI EN ISO 10545-05	Suggested Minimum: E > 0.55	Resistant	Resistant
0	Resistance to Deep Abrasion UNI EN ISO 10545-06	Maximum: 175 mm <sup>3</sup>	N/A	N/A
<u>←</u> () →	Thermal Linear Expansion UNI EN ISO 10545-08	As Reported	6.1 x 10/°C-6	6.1 x 10/°C-6
*	Thermal Shock Resistance UNI EN ISO 10545-09	Required	Resistant	Resistant
000	Moisture Expansion UNI EN ISO 10545-10	As Reported	≤0.01 mm/mm	≤0.01 mm/mm
券	Frost Resistance UNI EN ISO 10545-12	As Reported	Resistant	Non-Resistant
Ş	Chemical Resistance UNI EN ISO 10545-13	Domestic Chemical Products: UB/GB Acids and Alkalis: As Reported	GLB GLA   GHB	GLB GLA   GHB
*	Stain Resistance UNI EN ISO 10545-14	Minimum: Class 3	Class 4	Class 4
PEI	PEI Rating (Scratch Resistance) ASTM C 1027	As Reported	IV	IV
25 }	Dynamic Coefficient of Friction (DCOF) ANSI A137.1	For Level Interior Spaces Expected to be Walked Upon When wet: > 0.42	> 0.42	< 0.42
	Shade Variation	As Reported	V2	∨2
÷	Thickness	As Reported	3" x 12" - 8mm 12" x 24" - 8mm 24" x 24" - 9mm	3" x 12" - 8mm 12" x 24" - 8mm 24" x 24" - 9mm
⊞	Number of Screens	As Reported	3" x 12" - 182 12" x 24" - 26 24" x 24" - 13	3" x 12" - 182 12" x 24" - 26 24" x 24" - 13

Grout joint required for rectified edge tile







- 1/3 - Overlap should not exceed 33%

 Recommended 3/16" Grout Joint






## SUBLIME 2.0

WHITE BODY RECTIFIED PORCELAIN & CERAMIC









## SUBLIME 2.0

Sublime's marbleized veining comes pronounced just well enough, to give the room an essence of prestige, without overstating itself. This realistic approach to veining keeps harsh lines out of your room, while still giving flair.

Available in both a glossy and a natural finish, Sublime can find itself at home in kitchens, bathrooms, or any other room in the home



...

...

...

....

....

....